



# Acryrub

# Revision: 8/09/2015

# Page 1 from 2

#### **Technical data**

Basis	Acrylic dispersion
Consistancy	Paste
Curing system	Physical drying
Skin formation* (20°C / 65% R.H.)	Ca. 20 min
Density	Ca. 1,70 g/ml
Maximum allowed distortion	15 %
Temperature resistance	$-20 \ ^{\circ}C \rightarrow 80 \ ^{\circ}C$
Application temperature	$5 \ ^{\circ}C \rightarrow 30 \ ^{\circ}C$
Shrinkage	Ca. 15% (DIN 52451)

(\*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

#### **Product description**

Acryrub is a high-quality, plasto-elastic onecomponent joint sealant based on silanized acrylic dispersions. Acryrub is a onecomponent, quickly paintable, plasto-elastic sealant based upon acrylic dispersion. Due to its unique composition, it minimalizes the risk for crazing, even with highly filled and covering paints.

#### **Properties**

- Very easy to apply
- Colourfast and waterproof after curing
- Can be painted over after curing
- Very good adhesion on many porous surfaces and aluminium

# Applications

- Joints with movement till max. 15%
- Connection joints in building industry.
- Joints on window sills, between plinths and walls, between masonry, ...

#### Packaging

*Colour*: white, grey, brown, black *Packaging*: 310 ml cartridge, 600 ml sausage

#### Shelf life

At least 12 months in unopened packaging in a dry storage place at temperatures between +5°C and +25°C. Protect against frost.

#### Substrates

Substrates: all usual porous building substrates Nature: clean, free of dust and grease. Surface preparation: Highly porous surfaces should be primed with diluted Acryrub ( 1 part Acryrub + 2 parts water). Not suitable for natural stone, bitumen, glass and metal. We recommend a preliminary adhesion test on every surface.

#### Joint dimensions

*Min. width for joints*: 5 mm *Max. width for joints*: 20 mm *Min. depth for joints*: 5 mm Recommendation sealing jobs: joint width = joint depth. Use PE backer rods before applying the sealant in large joints to avoid 3point adhesion.

#### **Application method**

Do not apply when rain or frost is imminent during curing process. *Application method*: With manual- or pneumatic caulking gun. Finish with spatula or filling knife. *Cleaning*: Before curing, Acryrub can be removed with water from tiles and tools. *Finishing*: With a soapy solution or Soudal Finishing Solution before skinning. *Repair*: With the same material

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Everdongenlaan 18 - 20 Fax: +32 (0)14-42.65.14





# Revision: 8/09/2015

# Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult the packaging label for more information.

#### Remarks

- Do not use in applications where continuous water immersion is possible.
- Paintable with most paints.
- The paint must be sufficiently elastic to allow application on a plasto-elastic sealant.
- Given the great diversity in available paints it is recommended to do a compatibility test prior to application.

#### **Environmental clauses**

#### Leed regulation:

Acryrub conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED® 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Everdongenlaan 18 - 20 Fax: +32 (0)14-42.65.14 BE-2300 Turnhout www.soudal.com

## Page 2 from 2