



PRO 10D Wood Adhesive

Revision: 22/06/2015 Page 1 from 2

Technical data

Basis	PVAc
Consistancy	High viscous fluid
Curing system	Physical drying
Density	1,20 g/ml
Viscosity (Brookfield)	10.000 mPa.s → 18.000 mPa.s
Open time (*)	Ca. 15 min.
Pressing pressure	1 kg/cm ² → 2 kg/cm ²
Water resistance (EN204)	D1/D2
Consumption (*)	80 - 120 g/m² in full surface bonding.
	150 - 180 g/m² in assembly.
pH level	$6,0 \rightarrow 7,0$
Min. Film Forming Temperature (MFFT)	4 °C
Total solid content	Ca. 50 %

^(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

Product description

PRO 10D Wood Adhesive is a ready to use, fast drying, PVA-based wood adhesive.

Properties

- Easy to tool
- Semi-transparent when dry
- High end strength

Applications

- Bonding of all common wood connections
- Bonding of paper products

Packaging

Colour: white

Packaging: 750gr. 5 kg

Shelf life

At least 24 months in unopened packaging in a dry storage place at temperatures between +5°C and +25°C.

Substrates

Substrates: many porous substrates, wood, carton

Nature: The to be bonded materials should be flat and well fitting as well as clean, dry and free of dust and grease.

Surface preparation: Slightly grinding smooth non-porous surfaces can improve the adhesion.

We recommend a preliminary compatibility test.

Application method

Application method: Apply the adhesive with the aid of a fine-toothed comb or brush on one of the materials to be bonded. Join the parts together and clamp for 2 to 4 hours. Cleaning: Before curing, PRO 10D Wood Adhesive can be removed with water from tiles and tools. Cured PRO 10D Wood Adhesive can only be removed mechanically. Repair: With the same material

Health- and Safety Recommendations

Take the usual labour hygiene into account.

Consult label and material safety data sheet for more information.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 BE-2300 Turnhout

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com





PRO 10D Wood Adhesive

Revision: 22/06/2015 Page 2 from 2

Remarks

 When bonding certain types of oak and tropical wood staining can occur.

• Do not dilute the adhesive.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

 Soudal NV
 Everdongenlaan 18 - 20
 BE-2300 Turnhout

 Tel: +32 (0)14-42.42.31
 Fax: +32 (0)14-42.65.14
 www.soudal.com