

Declaration of Performance

No. DOP-01-CLA-02 / Page 1 of 4

Classic Multi-Purpose Screws



Material - Carbon Steel (C1022)

Head Type - Pan

Screw Diameter (mm) - 3.5, 4.0, 5.0

We hereby declare these designated products have performed initial type testing under system 3, Annex V of the regulation (EU) no. 305/2011 (Construction Products Regulation), with the reference to the harmonised European standard (hEN) BS EN 14592:2008+A1:2012 (Timber structures - Dowel type fasteners - Requirements) for screws intended for the use in "load bearing timber structures" and produced the calculation/test reports as attached;

The initial type testing has been carried out by independent notified body;
Strojirensky Zkusebni Ustav, NB # 1015, Hudcova 424/56B, 621 00 Brno-Medlánky, Czechia

Certificate Number: E-30-20009-13, E-30-20010-13, CPR-J-01417-21

Test Report Number: No. 30-9797/8, 30-9797/9, 30-15599/JP

Factory Process Control (FPC) has been established by the factory and independently audited by TUV Rheinland UK in accordance with ISO9001.

This declaration of conformity is valid until there is a significant change in the product and declared characteristics. ie. raw material or change in production process.

This declaration is the responsibility of the importer ; T.I.Midwood & Co. Ltd.

Simon Midwood

Managing Director

TIMCO House
2013

2013

Name

Position

Signature

Location & Date

Test Year

Declaration of Performance

No. DOP-01-CLA-02 / Page 2 of 4

Classic Multi-Purpose Screws

Pan Head - Ø3.5mm

Material & Geometry

Material	Carbon Steel (C1022)
Screw diameter (mm)	3.5
Head diameter (mm)	6.72
Inner thread diameter (mm)	2.25

Mechanical Strength & Stiffness

Characteristic yield moment $M_{y,k}$ at 18° [Nmm] (thread section) in acc. to EN 409	2490
Characteristic withdrawal parameter (loading across the fibre) $f_{ax,k}$ [N/mm²] in acc. to EN 1382 with density of wood $\rho_k = 390\text{kg/m}^3$	18.55
Characteristic withdrawal parameter (loading along the fibre) $f_{ax,k}$ [N/mm²] in acc. to EN 1382 with density of wood $\rho_k = 390\text{kg/m}^3$	11.04
Characteristic head pull-through parameter $f_{tens,k}$ [N/mm²] in acc. to EN 1383 with density of wood $\rho_k = 500\text{kg/m}^3$	45.75
Characteristic tensile capacity $f_{tens,k}$ [kN] in acc. to EN 1383	4.57
Characteristic torsional ratio in acc. to EN 15737 with density of wood $\rho_k = 450\text{kg/m}^3$	2.90

Durability

Coating (Finish)	Zinc or Yellow coating
Corrosion protection	Service Class 1 acc. to EN 1995-1-1

Declaration of Performance

No. DOP-01-CLA-02 / Page 3 of 4

Classic Multi-Purpose Screws

Pan Head - Ø4.0mm

Material & Geometry

Material	Carbon Steel (C1022)
Screw diameter (mm)	4.0
Head diameter (mm)	7.87
Inner thread diameter (mm)	2.50

Mechanical Strength & Stiffness

Characteristic yield moment $M_{y,k}$ at 17° [Nmm] (thread section) in acc. to EN 409	3648
Characteristic withdrawal parameter (loading across the fibre) $f_{ax,k}$ [N/mm ²] in acc. to EN 1382 with density of wood $\rho_k = 390\text{kg/m}^3$	17.85
Characteristic withdrawal parameter (loading along the fibre) $f_{ax,k}$ [N/mm ²] in acc. to EN 1382 with density of wood $\rho_k = 390\text{kg/m}^3$	11.52
Characteristic head pull-through parameter $f_{tens,k}$ [N/mm ²] in acc. to EN 1383 with density of wood $\rho_k = 500\text{kg/m}^3$	33.61
Characteristic tensile capacity $f_{tens,k}$ [kN] in acc. to EN 1383	5.99
Characteristic torsional ratio in acc. to EN 15737 with density of wood $\rho_k = 450\text{kg/m}^3$	3.45

Durability

Coating (Finish)	Zinc or Yellow coating
Corrosion protection	Service Class 1 acc. to EN 1995-1-1

Declaration of Performance

No. DOP-01-CLA-02 / Page 4 of 4

Classic Multi-Purpose Screws

Pan Head - Ø5.0mm

Material & Geometry

Material	Carbon Steel (C1022)
Screw diameter (mm)	5.0
Head diameter (mm)	9.68
Inner thread diameter (mm)	3.02

Mechanical Strength & Stiffness

Characteristic yield moment $M_{y,k}$ at 14° [Nmm] (thread section) in acc. to EN 409	8241
Characteristic withdrawal parameter (loading across the fibre) $f_{ax,k}$ [N/mm ²] in acc. to EN 1382 with density of wood $\rho_k = 350\text{kg/m}^3$	16.01
Characteristic withdrawal parameter (loading along the fibre) $f_{ax,k}$ [N/mm ²] in acc. to EN 1382 with density of wood $\rho_k = 350\text{kg/m}^3$	13.92
Characteristic head pull-through parameter $f_{tens,k}$ [N/mm ²] in acc. to EN 1383 with density of wood $\rho_k = 350\text{kg/m}^3$	27.28
Characteristic tensile capacity $f_{tens,k}$ [kN] in acc. to EN 1383	9.20
Characteristic torsional ratio in acc. to EN 15737 with density of wood $\rho_k = 450\text{kg/m}^3$	5.21

Durability

Coating (Finish)	Zinc or Yellow coating
Corrosion protection	Service Class 1 acc. to EN 1995-1-1